



**Colorimetric Parameters**

Chromaticity Coordinate:  $x=0.3843$   $y=0.3932$   $u'=0.2212$   $v'=0.5092$   
 CCT=4014K (Duv=0.0064) Dominant WL:Ld =576.1nm Purity=33.4%  
 Peak WL:Lp=592.0nm FWHM=153.4nm  
 Render Index:Ra=82.1  
 R1 =79 R2 =87 R3 =94 R4 =83 R5 =80 R6 =83 R7 =87  
 R8 =64 R9 =3 R10=70 R11=82 R12=63 R13=81 R14=97 R15=72

**Photometric & Radiometric Parameters**

Flux=1188 lm Eff.:123.79 lm/W Fe=3.530 W

**Electrical parameters**

V=24.00 V I=0.4000 A P=9.600 W PF=1.000 F=0.00 Hz

Status: Integral T = 88 ms Ip = 55763 (85%)  
 Test Mode: Fast Test; Sensitivity = High; Tecool: ON

Model:FD1282408NO  
 Test By:JYH  
 Temperature:25.3Deg  
 Manufacturer:COLORS  
 Assessor:damin

Number:2  
 Date:2021-01-08 16:32:00  
 Humidity:65.0%  
 Remarks:FD1282408NO-8NWSA012BC0100  
 Brand:SN:

# TM30

